

RANGER BOARD

PREMIUM PLUS MDF SPECIFICATIONS



MDF Properties (Imperial)	3/8" - 1/2"	9/16" - 7/8"	15/16" - 1 1/4"
Density	49 pcf	49 pcf	48 pcf
Internal Bond	140 psi	140 psi	130 psi
Modulus of Rupture	5,000 psi	5,000 psi	5,000 psi
Modulus of Elasticity	500,000 psi	500,000 psi	500,000 psi
Screw Holding-Face	450 lbs	450 lbs	450 lbs
Screw Holding-Edge	N/A	425 lbs	425 lbs
Thickness Swell	0.065 in.	7%	4%
Linear Expansion	0.3%		
Thickness Tolerance	± 0.005 in.		
Moisture Content	4-6%		

MDF Properties (Metric)	9mm-12mm	14mm-22mm	23mm-32mm
Density	785 kg/m ³	785 kg/m ³	769 kg/m ³
Internal Bond	0.97 N/mm ²	0.97 N/mm ²	0.90 N/mm ²
Modulus of Rupture	34.5 N/mm ²	34.5 N/mm ²	34.5 N/mm ²
Modulus of Elasticity	3,450 N/mm ²	3,450 N/mm ²	3,450 N/mm ²
Screw Holding-Face	2,000 N	2,000 N	2,000 N
Screw Holding-Edge	N/A	1,890 N	1,890 N
Thickness Swell	1.65mm	7%	4%
Linear Expansion	0.3%		
Thickness Tolerance	± 0.127mm		
Moisture Content	4-6%		

- Ranger Board is certified with:
 - Composite Panel Association Eco-Certified Composite Grademark Certification Program (ECC 4-19) and ANSI A208.2 – 2016
 - Scientific Certification Services (SCS – MC – 01444)
 - Forest Stewardship Council Standard for Chain of Custody Certification (FSC-STD-40-004 v2-1) and the Standard for Company Evaluation of FSC Controlled Wood (FSC-STD-40-005 v2-1)
- Formaldehyde emissions: Ranger Board MDF – EPA TSCA Title VI, CARB ATCM 93120.
- Surface Burning Characteristics: Testing completed on Ranger Board MDF, show material being Class III or C in accordance with ULC Standard CAN/ULC-S102.
- Standard finish 150 grit
- Finished sizes available:
 - Width: 48" to 73"
 - Length: 48" to 205"
 - Other sizes available upon request.
- All physical property values represent the compiled average of quality assurance testing conducted on Ranger Premium Plus MDF.
- Ranger Premium Plus MDF complies with ANSI A208.2 – 2016 using the prescribed test methods in ASTM D-1037.
- Ranger Premium Plus MDF is manufactured from 100% Western white softwoods. Appearance is a consistent light sandy color.

Ranger Board, a Division of West Fraser Mills Ltd.
 1250 Brownmiller Rd.
 Quesnel, B.C. V2J 6P5
 General sales phone #: 250-992-9254
 General email: mdf@westfraser.com
 (2019)



West Fraser